

DTIC FILE COPY

12

**AD-A233 535**

OFFICE OF NAVAL RESEARCH

Contract: N00014-85-K-0222

Work Unit: 4327-555

Scientific Officer: Dr. Richard S. Miller

Technical Report No. 27

EFFECT OF TEMPERATURE AND OXYGEN ON THE STRENGTH OF ELASTOMERS

by

A. N. Gent, Ginger L. Liu and T. Sueyasu

Institute of Polymer Engineering

The University of Akron

Akron, Ohio, 44325-0301

March, 1991



Reproduction in whole or in part is permitted for any purpose  
of the United States Government.

Approved for public release; distribution unrestricted.

91 3 19 107

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report No. 27	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) EFFECT OF TEMPERATURE AND OXYGEN ON THE STRENGTH OF ELASTOMERS		5. TYPE OF REPORT & PERIOD COVERED Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) A. N. Gent, G. L. Liu and T. Sueyasu		8. CONTRACT OR GRANT NUMBER(s) N00014-85-K-0222
9. PERFORMING ORGANIZATION NAME AND ADDRESS Institute of Polymer Engineering The University of Akron Akron, OH 44325-0301		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 4327-555
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Power Program Arlington, VA 22217-5000		12. REPORT DATE March 1991
		13. NUMBER OF PAGES 39
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) According to attached distribution list. Approved for public release; distribution unrestricted.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Submitted to: Rubber Chemistry and Technology		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Crack growth, Elastomers, Fatigue, Fracture, Rubber, Strength, Tear strength, Temperature		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Measurements have been made of the tear energy $G$ of SBR and BR vulcani- zates as a function of rate of tearing, temperature, and air pressure. Approximately linear relations were obtained between the logarithm of the rate of tearing at a fixed energy input and the reciprocal of absolute temperature, over the range 25° to 130°C. Apparent activation energies		

## 20. ABSTRACT continued

of 20 to 32 kcal/mole were deduced for the tear strength, much larger than predicted by the WLF relation for changes in viscous losses with temperature far above  $T_g$ . Another temperature-dependent term in the tear strength is therefore inferred. It is suggested that threshold strength,  $G_0$ , measured in the absence of viscous effects, is itself temperature-dependent. Changes in  $G_0$  by factors of between 2X and 5X as the temperature is reduced from 130° to 25°C would account for the observed discrepancies. Tear rates were also measured under either steady loading or intermittently-applied loads as a function of atmospheric pressure, over the range of 0.1 to 760 mm Hg. They were found to decrease to about 25-30% of the values at one atmosphere, on removing air almost completely. This effect of air pressure is attributed to attack of oxygen (in air) on highly-stressed bonds, either sulfidic or hydrocarbon in nature, accelerating the tear process.

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail. and/or Special
A-1	



# Effect of Temperature and Oxygen on the Strength of Elastomers

A. N. Gent, Ginger L. Liu and T. Sueyasu<sup>1</sup>

Institute of Polymer Engineering

The University of Akron, Akron, Ohio 44325-0301

## 1. Introduction

Crack growth occurs in rubber vulcanizates under stress when a sufficient amount of elastically-stored energy  $\underline{W}$  is released by growth of the crack. The criterion is (1):

$$-(\partial W / \partial S)_d \geq G_c \quad (1)$$

where  $\underline{S}$  is the area torn through by the crack and  $\underline{G}_c$  is the energy required for tearing through unit area ( $\text{J/m}^2$ ), a measure of strength. The derivative on the left-hand side of Equation 1 is taken under conditions of constant displacement  $\underline{d}$ , to avoid the complexity of further work input as the crack grows.

It is found, in practice, that the value of  $\underline{G}_c$  is not well-defined. Cracks grow to some extent when the available energy  $\underline{G}$ , defined by the left-hand side of Equation 1, exceeds a threshold level  $\underline{G}_0$ , of the order of  $50 \text{ J/m}^2$  (2,3). The amount of crack growth then depends upon the extent to which  $\underline{G}$  exceeds the threshold level. It is only at a much higher level, denoted here  $\underline{G}_c$ , of the order of  $10,000 \text{ J/m}^2$ , that catastrophic tearing occurs.

-----

<sup>1</sup>On leave of absence from Bridgestone Corporation, Japan.

The slow or small-scale tearing that takes place for stresses corresponding to values of  $\underline{G}$  between these two limits,  $\underline{G}_0$  and  $\underline{G}_c$ , is referred to as mechanical fatigue cracking. It is more pronounced under intermittently-applied loads, but for non-crystallizing elastomers, such as SBR, steady tearing takes place if the load is maintained continuously, at a slower rate. For a wide range of applied loads and tearing energies  $\underline{G}$ , the rate of crack propagation  $\underline{dc}/\underline{dt}$ , where  $\underline{t}$  is the duration of steady loading, or  $\underline{dc}/\underline{dn}$ , where  $\underline{n}$  is the number of load applications, is found to increase with  $\underline{G}$  in accordance with empirical power laws:

$$\underline{dc}/\underline{dt} = A \underline{G}^{\alpha} \quad (2)$$

or

$$\underline{dc}/\underline{dn} = A' \underline{G}^{\alpha'} \quad (3)$$

where the exponents  $\underline{\alpha}$  and  $\underline{\alpha}'$  are found to be about 4 for SBR and 5 to 6 for BR. The crack growth constants for steady tearing ( $\underline{A}$ ) and intermittent tearing ( $\underline{A}'$ ) are characteristic of the compound and the test conditions (4).

In fact, although the test conditions, notably the test temperature and the presence or absence of air, are known to have large effects on the rate of crack propagation, there is relatively little quantitative information available, especially at high

temperatures. We have therefore studied these effects in detail for three well-defined vulcanizates of SBR, having different types of crosslink, and a sulfur vulcanizate of BR. The results are reported here.

## 2. Experimental

Pure shear testpieces were used, shown in Figure 1, for the measurements on SBR, with a length of 180 mm, a width of 34 mm and a central thickness of about 0.75 mm. They were bonded to long metal end-pieces, one of which was held fixed and the other was fastened to a moveable clamp. An initial cut was made along the center line of the specimen from one end, about 40 mm long. The moveable end-piece was then pulled away from the stationary one, either to a fixed distance, putting the specimen under a pre-determined pure shear strain, or cycled between the unstrained position and a pre-determined position, subjecting the specimen to an intermittent pure shear strain. In the first case the specimen was under a constant pure shear strain and in the second it was strained intermittently, at a frequency of 1.8 Hz.

For these samples the tearing energy  $\underline{G}$  is given by (1,5)

$$G = W'/t_0 \quad (4)$$

where  $t_0$  is the thickness of the central part of the test specimen and  $\underline{W'}$  is the amount of elastic energy stored in the specimen per unit length. Values of  $\underline{W'}$  were determined from experimental

relations between applied load and displacement for each specimen. Because Equation 4 does not contain the length  $c$  of the crack, the tear energy, and hence the rate of growth of a crack, is in principle constant for pure shear test specimens. This is a considerable experimental advantage.

Rates of crack growth were measured at various values of the average applied strain  $\epsilon$ , given by the ratio  $d/h_0$  of displacement  $d$  to unstrained width  $h_0$ . The test chamber could be evacuated to a low pressure of air by means of a vacuum pump, and heated by radiant heaters.

Measurements on a BR vulcanizate were carried out by propagating a tear through a thin strip, about 1 mm thick, at a constant speed, and measuring the average tearing force  $F$ . In this case the tearing energy  $G$  is given by (1)

$$G = 2F/t \quad (5)$$

where  $t$  is the width of the torn path, measured after tearing. The value of  $t$  was generally 50% larger than the thickness of the sheet because the tear tended to run at an angle of about  $45^\circ$  to the plane of the sheet (6).

The compounds used are given in Table 1. For SBR they were chosen to give: SBR-1, C-C crosslinks; SBR-2, mainly monosulfidic crosslinks; and SBR-3, mainly polysulfidic crosslinks. Crosslinking was effected by heating for 1 h at  $150^\circ\text{C}$ . For BR a standard sulfur recipe was used, crosslinked for 50 min at  $140^\circ\text{C}$ .

### 3. Results and discussion

#### (a) The effect of air pressure for SBR

Various air pressures were used, in the range: 0.01 mm Hg to 760 mm Hg (one atmos.). Results for SBR-2 are shown in Figures 2 and 3. Over a wide range of values of tearing energy  $G$  the rates of crack growth under steady and intermittent loading were in good agreement with Equations 2 and 3, with values of the exponents  $\alpha$  and  $\alpha'$  of 4.3 and 3.4, respectively. In all cases they were lower at low air pressures, by a constant factor, independent of the tear energy. Thus, removing air completely has the same proportionate effect on slow and fast rates of crack growth, reducing them to about 30% of the values at one atmosphere of air in the case of intermittent loading and to about 25% in the case of steady loading.

There was some indication that the effect of air pressure disappeared at extremely low air pressures, below about 1 mm Hg, for intermittent loading, Figure 5, but this feature was not apparent in the measurements under continuous loading, Figure 4. In any case, the major changes occurred between 0.001 and 1 atmos, and over this range the linear relations shown in Figures 4 and 5 have the same slope, about 0.12. Thus, the effect of atmospheric pressure appears to be independent of the level of stress or whether it is intermittent or continuously applied. It can be described by the empirical relations:

$$dc/dt = AG^{\alpha} (P/P_0)^{\beta} \quad (6)$$



and

$$dc/dn = A' G^{\alpha'} (P/P_0)^{\beta} \quad (7)$$

over the pressure range from  $P = 0.001$  atmos up to the reference pressure  $P_0$  ( $= 1$  atmos), where  $\beta = 0.12$  for compound 2.

Experiments with SBR-1 and SBR-3 under continuous loading yielded values for the exponent  $\beta$  of 0.082 and 0.185, respectively. Thus, the compound with C-C crosslinks is the least affected by the atmospheric pressure, the one with mainly monosulfidic crosslinks is more strongly affected and the compound with mainly polysulfidic crosslinks is the most affected. These observations are consistent with the known susceptibility of these materials to oxidation.

#### (b) Effect of temperature for SBR

Values of the rate of crack growth  $dc/dt$  for SBR-3 under steady tearing conditions were determined over the temperature range:  $25^{\circ}\text{C}$  to  $100^{\circ}\text{C}$ . The results are plotted in Figures 6 and 7 on logarithmic scales against the reciprocal of the test temperature  $T$ . The results shown in Figure 6 were obtained at an air pressure of one atmos; those in Figure 7 were obtained at a reduced pressure of 0.1 mm Hg. In both cases they show a strong dependence on temperature, the relations being approximately parallel for different values of the imposed average strain at  $25^{\circ}\text{C}$ . Thus, the rate of crack growth appears to depend exponentially upon the reciprocal of temperature, with an apparent activation energy  $E$

which is independent of applied stress:

$$dc/dt = AG^{\alpha}(P/P_0)^{\beta} \exp(-E/R)[(1/T) - (1/T_0)] \quad (8)$$

where the reference temperature  $T_0$  is ambient temperature (298°K).

It should be noted that these measurements were made using a fixed displacement of the specimen clamps. Because a significant amount of thermal expansion occurred when the temperature was raised, the strain energy stored in the specimen at a given displacement became smaller and the amount of energy  $G$  available for tearing was correspondingly reduced. However, experimentally-determined relations between stress (and strain energy  $G$  available for tearing) and the average strain measured at that temperature were found to be substantially the same over the temperature range 20°C to 80°C. Values of average strain, and hence  $G$ , were therefore computed from the observed values of the unstretched width  $h_0$  at each temperature. They were employed to calculate best-fit constants in Equation 8. Values obtained in this way for SBR-3 are given in Table 2. Relations corresponding to Equation 8 with these values of the constants are represented by the full curves of Figures 6 and 7. They are seen to describe the experimental results with reasonable accuracy.

Experiments were also carried out at various temperatures with the clamp displacements chosen so as to give constant values for tearing energy, i.e., making allowance for thermal expansion of the test specimen. Measured values of the rate of crack growth are

plotted in Figure 8 against the reciprocal of the test temperature, for two different values of tearing energy  $G$ . The full lines in Figure 8 were calculated from Equation 8, using the fitting constants given in Table 2. They are seen to describe the experimental results well. Furthermore, there is no significant difference in the values of the fitting constants at 1 atmos and at 0.1 mm Hg. Thus, it is clear that Equation 8 represents the rate of crack growth of this vulcanizate over a wide range of applied loads, test temperatures and air pressures. The effects of these variables are apparently independent and multiplicative, to a first approximation.

Similar measurements of the rate of steady tearing were made for SBR-1. The results are shown in Figures 9 and 10. A value for activation energy  $E$  of  $25 \pm 2$  kcal/mole was obtained from them, substantially less than the value of  $32 \pm 3$  kcal/mole deduced for SBR-3 but considerably higher than would be expected from the WLF relation that accounts for changes in viscous energy losses with temperature. The effective activation energy from the WLF rate-temperature equivalence would be about 17 kcal/mole for SBR (with a glass transition temperature of  $-55^{\circ}\text{C}$ ) over the present temperature range.

Resistance to tearing has been attributed mainly to internal energy dissipation as the material is deformed to the point of rupture (7). Evidence for this is the good correlation obtained between tear energy  $G$  and the value of the out-of phase shear modulus  $G''$ , a measure of internal dissipation (7). Moreover,

provided care is taken to prevent the tear becoming rougher at lower temperatures or higher rates of tearing, experimental relations between tear energy and tear rate are found to follow temperature shifts in good agreement with the predictions of the WLF relation for segmental mobility as a function of temperature (7,8). Similarly, the tensile strength and extensibility of a simple SBR vulcanizate depend upon rate of stretching and temperature as expected for viscous processes (9).

But these studies of tearing and tensile strength have been largely carried out at low temperatures, near the glass temperature  $T_g$ , and at temperatures up to about  $100^{\circ}\text{C}$  above  $T_g$ , where changes in molecular mobility and internal energy dissipation are most pronounced. For example, tear strength results reported previously for an SBR vulcanizate were found to be in good accord with the predictions of the WLF relation over a wide temperature range, from  $-40$  to  $+100^{\circ}\text{C}$  (8). On closer inspection, however, the results at the higher temperatures,  $25^{\circ}$  to  $100^{\circ}\text{C}$ , are in better agreement with an activation energy of 27 to 32 kcal/mole, as in the present measurements, rather than with the lower value, about 17 kcal/mole expected from the WLF relation.

Thus, there is reason to question the applicability of the WLF rate-temperature equivalence to tear strength results at high temperatures. In an attempt to clarify this point, measurements have also been carried out on a BR vulcanizate, with a much lower glass transition temperature,  $-96^{\circ}\text{C}$ . The equivalent activation energy for viscous processes at temperatures in the range 25 to

130°C is obtained from the WLF relation as only about 10 kcal/mole in this case. Only small effects of temperature on the tear strength would therefore be expected. The experimental results are described in the following section.

(c) Effect of temperature for a BR vulcanizate

Measured tear strengths are plotted against the rate of tearing in Figure 11, using logarithmic scales for both axes. Although the results do not fall on strictly parallel curves, it is possible to obtain shift factors  $\log a_T$  by superimposing them as closely as possible at a given value of tear energy  $G$ . The results are plotted in Figure 12 as a function of the reciprocal of absolute temperature, in order to obtain an effective activation energy from the slope. A value was obtained in this way of about 18-20 kcal/mole, much larger than expected for a purely viscous process over this temperature range. Thus, as found for the SBR vulcanizates, there is a marked discrepancy between the observed temperature dependence of tear energy and that predicted by the WLF relation.

We are therefore led to conclude either that the WLF relation seriously underestimates the changes in viscous energy losses with temperature at high temperatures, or that there is an additional temperature-dependent part of the tear strength that does not obey the WLF relationship. The latter alternative seems more likely. A possible origin of the second term in tear strength is discussed in the following section.

(d) Possible temperature dependence of  $\underline{G}_0$

The tear energy  $\underline{G}$  can be expressed as the sum of two terms, an inherent, "threshold" strength  $\underline{G}_0$  that exists in the absence of any dissipative process, and a term  $\underline{H}\underline{G}_0$  due to internal energy losses that are generated in deforming the sample to the point of rupture (10):

$$G = G_0 (1 + H) \quad (9)$$

where  $\underline{H}$  is generally much greater than unity. The factor  $\underline{H}$ , and hence the term in parentheses, is expected to follow the WLF rate-temperature equivalence for simple visco-elastic solids. We now consider a separate temperature dependence of the threshold strength  $\underline{G}_0$ , independent of the rate of tearing.

By subtracting rate-temperature shifts  $\log a_T$  calculated from the universal form of the WLF relation, from the experimentally-observed ones, and applying a shift in  $\log \underline{G}$ , denoted  $\Delta \log \underline{G}_0$ , to account for the discrepancy, Figure 13, values were obtained for  $\Delta \log \underline{G}_0$  that depend on temperature as shown in Figure 14. They decreased markedly with temperature, from 2X - 5X at 25°C down to 1X at the reference temperature of 130°C. They are rather similar in general form for the different materials, even though the overall dependences of tear energy upon temperature were quite different.

Previous measurements of the threshold tear energy  $G_0$ , carried out mainly at high temperatures, have given values of about 50 J/m<sup>2</sup>. If the inferred changes in  $G_0$  are applied to this value, assumed to hold at 130°C, they yield a dependence of  $G_0$  on temperature from 100 - 250 J/m<sup>2</sup> at 25°C to 50 J/m<sup>2</sup> at 130°C. This decrease may reflect the thermal sensitivity of sulfur crosslinks (11,12).

For vulcanizates of both polymers the anomalously strong dependence of tear energy upon temperature at high temperatures can be accounted for as a sum of two effects: a viscous-loss contribution that decreases with temperature in accordance with the WLF relation, and a decrease in the "intrinsic" strength of the molecular network.

But it should be pointed out that the magnitudes estimated here for  $G_{0,T}$  (Figure 14) are quite approximate. They are based on relatively imprecise measurements of tear strength over limited ranges of rate and temperature, that are then compared with extrapolations of the WLF relation. Nevertheless, the values obtained seem inherently plausible.

They lead to an important conclusion, that the threshold strength itself will become large at low temperatures. Relatively few direct measurements have been made of threshold strength, and they have usually been carried out at high temperatures, to approach non-dissipative conditions. Thus, no direct evidence is known to the present authors of a significant temperature

dependence of  $G_0$ . However, if it is, indeed, the case that  $G_0$  increases as the temperature is lowered, then the observed tear strength will be expected to rise rapidly (as is observed) because the effect is coupled with a simultaneous rise in dissipative processes, Equation 9.

Moreover, different temperature dependences will be expected for different polymers. Similarly, the effect of temperature on tear strength will presumably be different for materials with different crosslinking systems, even when viscous effects are the same. Further experimental studies are needed in this area.

#### 4. Conclusions

1. A linear relationship has been found to hold for SBR vulcanizates between the logarithm of the rate of steady tearing and the logarithm of the air pressure, over the range 0.1 mm Hg to 760 mm Hg. The slope varied from 0.08 for a C-C crosslinked material to 0.18 for a polysulfide-crosslinked material. Similar effects of air pressure were found in the rate of crack propagation under intermittent loading. They are attributed to attack of oxygen (in air) on highly stressed bonds, either sulfidic or hydrocarbon.

2. Approximately linear relationships were found to hold between the logarithm of the rate of steady tearing and the reciprocal of the test temperature for temperatures between 25°C and 130°C. Apparent activation energies were deduced from the slopes, of 32



kcal/mole for a polysulfide-crosslinked SBR compound, 25 kcal/mole for a C-C crosslinked SBR compound, and 20 kcal/mole for a sulfur vulcanizate of BR. For SBR, these values were independent of the air pressure.

3. These activation energies are far too large to be accounted for by changes in segmental mobility (and hence in internal energy dissipation) with temperature, for simple visco-elastic materials at temperatures far above  $T_g$ . The discrepancies are attributed to a second temperature-dependent factor. It is suggested that the threshold tear strength  $G_0$ , i.e., the strength under non-dissipative conditions, is itself temperature dependent.

4. Estimates of the changes in  $G_0$  with temperature have been obtained from the observed discrepancies in temperature dependence of tear strength. They correspond to a decrease from about 100 - 250 J/m<sup>2</sup> at 25°C to about 50 J/m<sup>2</sup> at 130°C. These changes in  $G_0$  may reflect the stress-activated rupture of thermally-sensitive bonds.

#### Acknowledgements

This work forms part of a program of research on the strength of elastomers supported by the Office of Naval Research (Contract No. N00014-85-K-0222: Project Officer, Dr.R.S.Miller). The authors are also indebted to Lord Corporation and 3M Company for grants-in-aid, and to Bridgestone Corporation for awarding a leave of absence to T.S.

## References

1. R. S. Rivlin and A. G. Thomas, J. Polymer Sci. 10, 291 (1953).
2. G. J. Lake and P. B. Lindley, J. Appl. Polymer Sci. 9, 1233 ((1965)).
3. H. K. Mueller and W. G. Knauss, Trans.Soc.Rheol. 15, 217 (1971).
4. G. J. Lake and P. B. Lindley, Rubber J. Internatl. Plast. 146, Nos. 10 and 11, pp. 24, 30 (1964).
5. A. N. Gent and M. Hindi, Rubber Chem. Technol. 63, 123 (1990).
6. A. Ahagon, A. N. Gent, H. J. Kim and Y. Kumagai, Rubber Chem. Technol. 48, 896 (1975).
7. L. Mullins, Trans. Instn. Rubber Ind. 35, 213 (1959).
8. A. N. Gent and A. W. Henry, Proc. Internatl. Rubber Conf., Brighton, 1967, pp.193-204 (1968).
9. T. L. Smith, J. Polymer Sci. 32, 99 (1958).
10. A. N. Gent and C. T. R. Pulford, "Wear and Tear of Rubber", Chap. 5 in "Developments in Polymer Fracture - 1", ed. by E. H. Andrews, Appl. Sci. Publishers, Londonb, 1979, pp. 155-181.
11. J. R. Dunn, J. Scanlan and W. F. Watson, Trans. Faraday Soc. 55, 667 (1959).
12. S. Tamura and K. Murakami, Polymer 14, 569 (1973).

Table 1. Compound formulations.

	SBR-1	SBR-2	SBR-3	BR
SBR 1502	100	100	100	-
Diene 55	-	-	-	100
Stearic Acid	-	2	2	2
Zinc Oxide	-	5	5	5
Sulfur	-	-	2	2
SANTOCURE <sup>(a)</sup>	-	-	-	1
MOR <sup>(b)</sup>	-	-	1	-
TMTD <sup>(c)</sup>	-	4	-	-
DCP <sup>(d)</sup>	0.5	-	-	-

(a) N-cyclohexyl-2-benzothiazolesulfenamide.

(b) 2-(Morpholiniothio)benzothiazole.

(c) Tetra methylthiuramdisulfide.

(d) Dicumyl peroxide.

Table 2. Fitting constants in Equation 8.

	log A at 25°C ( SI units )	$\alpha$	E (kcal/mole)
SBR-1			
1 atm.	-14.6	3.5±0.5	25±2
0.1 mmHg	-14.5	3.6±0.5	25±2
SBR-3			
1 atm.	-18.9	4.4±0.5	32±3
0.1 mmHg	-18.6	4.4±0.5	32±3
BR			
1 atm.	-25.1	7.3±0.7	19±1

### Figure Legends

1. Test specimen
2. Experimental relations between the rate  $\frac{dc}{dt}$  of steady tearing and tear energy  $G$  for SBR-2 at different air pressures.
3. Experimental relations between the rate  $\frac{dc}{dn}$  of intermittent tearing and tear energy  $G$  for SBR-2 at different air pressures.
4. Experimental relations between the rate  $\frac{dc}{dt}$  of steady tearing and air pressure  $P$  for SBR-2 at various tear energies  $G$ .
5. Experimental relations between the rate  $\frac{dc}{dn}$  of intermittent tearing and air pressure  $P$  for SBR-2 at various tear energies  $G$ .
6. Effect of temperature on the rate  $\frac{dc}{dt}$  of steady tearing of SBR-3 at 1 atmos air pressure.
7. Effect of temperature on the rate  $\frac{dc}{dt}$  of steady tearing of SBR-3 at 0.1 mm Hg air pressure.
8. Effect of temperature on the rate  $\frac{dc}{dt}$  of steady tearing of SBR-3 at constant tear energy  $G$ .
9. Effect of temperature on the rate  $\frac{dc}{dt}$  of steady tearing of SBR-1 at 1 atmos air pressure.
10. Effect of temperature on the rate  $\frac{dc}{dt}$  of steady tearing of SBR-1 at 0.1 mm Hg air pressure.
11. Effect of temperature on the tear strength  $G$  of a BR compound, torn at various rates.
12. Shift factors  $\log a_T$ , from the results shown in Figure 11, plotted against the reciprocal of temperature.

13. Method of determining  $\Delta \log G_0$  from the experimental relations shown in Figure 11.

14. Dependence of  $\Delta G_0$  upon temperature for SBR-1, SBR-3 and BR vulcanizates.




FIGURE 1




FIGURE 2






FIGURE 3




FIGURE 4




FIGURE 5




FIGURE 6




FIGURE 7




FIGURE 8




FIGURE 9




FIGURE 10






FIGURE 11




FIGURE 12




FIGURE 13




FIGURE 14

(DYN)

DISTRIBUTION LIST

Dr. R.S. Miller  
Office of Naval Research  
Code 432P  
Arlington, VA 22217  
(10 copies)

Dr. J. Pastine  
Naval Sea Systems Command  
Code 06R  
Washington, DC 20362

Dr. Merrill K. King  
Atlantic Research Corp.  
5390 Cherokee Avenue  
Alexandria, VA 22312

Dr. R.L. Lou  
Aerojet Strategic Propulsion Co.  
Bldg. 05025 - Dept 5400 - MS 167  
P.O. Box 15699C  
Sacramento, CA 95813

Dr. R. Olsen  
Aerojet Strategic Propulsion Co.  
Bldg. 05025 - Dept 5400 - MS 167  
P.O. Box 15699C  
Sacramento, CA 95813

Dr. Randy Peters  
Aerojet Strategic Propulsion Co.  
Bldg. 05025 - Dept 5400 - MS 167  
P.O. Box 15699C  
Sacramento, CA 95813

Dr. D. Mann  
U.S. Army Research Office  
Engineering Division  
Box 12211  
Research Triangle Park, NC 27709-2211

Dr. L.V. Schmidt  
Office of Naval Technology  
Code 07CT  
Arlington, VA 22217

JHU Applied Physics Laboratory  
ATTN: CPIA (Mr. T.W. Christian)  
Johns Hopkins Rd.  
Laurel, MD 20707

Dr. R. McGuire  
Lawrence Livermore Laboratory  
University of California  
Code L-324  
Livermore, CA 94550

P.A. Miller  
736 Leavenworth Street, #6  
San Francisco, CA 94109

Dr. W. Moniz  
Naval Research Lab.  
Code 6120  
Washington, DC 20375

Dr. K.F. Mueller  
Naval Surface Weapons Center  
Code R11  
White Oak  
Silver Spring, MD 20910

Prof. M. Nicol  
Dept. of Chemistry & Biochemistry  
University of California  
Los Angeles, CA 90024

Mr. L. Roslund  
Naval Surface Weapons Center  
Code R10C  
White Oak, Silver Spring, MD 20910

Dr. David C. Sayles  
Ballistic Missile Defense  
Advanced Technology Center  
P.O. Box 1500  
Huntsville, AL 35807

(DYN)

DISTRIBUTION LIST

Mr. R. Geisler  
ATTN: DY/MS-24  
AFRPL  
Edwards AFB, CA 93523

Naval Air Systems Command  
ATTN: Mr. Bertram P. Sobers  
NAVAIR-320G  
Jefferson Plaza 1, RM 472  
Washington, DC 20361

R.B. Steele  
Aerojet Strategic Propulsion Co.  
P.O. Box 15699C  
Sacramento, CA 95813

Mr. M. Stosz  
Naval Surface Weapons Center  
Code R10B  
White Oak  
Silver Spring, MD 20910

Mr. E.S. Sutton  
Thiokol Corporation  
Elkton Division  
P.O. Box 241  
Elkton, MD 21921

Dr. Grant Thompson  
Morton Thiokol, Inc.  
Wasatch Division  
MS 240 P.O. Box 524  
Brigham City, UT 84302

Dr. R.S. Valentini  
United Technologies Chemical Systems  
P.O. Box 50015  
San Jose, CA 95150-0015

Dr. R.F. Walker  
Chief, Energetic Materials Division  
DRSMC-LCE (D), B-3022  
USA ARDC  
Dover, NJ 07801

Director  
US Army Ballistic Research Lab.  
ATTN: DRXBR-IBD  
Aberdeen Proving Ground, MD 21005

Commander  
US Army Missile Command  
ATTN: DRSMI-RKL  
Walter W. Wharton  
Redstone Arsenal, AL 35898

Dr. Ingo W. May  
Army Ballistic Research Lab.  
ARRADCOM  
Code DRXBR - 1BD  
Aberdeen Proving Ground, MD 21005

Dr. E. Zimet  
Office of Naval Technology  
Code 071  
Arlington, VA 22217

Dr. Ronald L. Derr  
Naval Weapons Center  
Code 389  
China Lake, CA 93555

Lee C. Estabrook, P.E.  
Morton Thiokol, Inc.  
P.O. Box 30058  
Shreveport, Louisiana 71130

Dr. J.R. West  
Morton Thiokol, Inc.  
P.O. Box 30058  
Shreveport, Louisiana 71130

Dr. D.D. Dillehay  
Morton Thiokol, Inc.  
Longhorn Division  
Marshall, TX 75670

G.T. Bowman  
Atlantic Research Corp.  
7511 Wellington Road  
Gainesville, VA 22065

(DYN)

DISTRIBUTION LIST

R.E. Shenton  
Atlantic Research Corp.  
7511 Wellington Road  
Gainesville, VA 22065

Mike Barnes  
Atlantic Research Corp.  
7511 Wellington Road  
Gainesville, VA 22065

Dr. Lionel Dickinson  
Naval Explosive Ordnance  
Disposal Tech. Center  
Code D  
Indian Head, MD 20340

Prof. J.T. Dickinson  
Washington State University  
Dept. of Physics 4  
Pullman, WA 99164-2814

M.H. Miles  
Dept. of Physics  
Washington State University  
Pullman, WA 99164-2814

Dr. T.F. Davidson  
Vice President, Technical  
Morton Thiokol, Inc.  
Aerospace Group  
3340 Airport Rd.  
Ogden, UT 84405

Mr. J. Consaga  
Naval Surface Weapons Center  
Code R-16  
Indian Head, MD 20640

Naval Sea Systems Command  
ATTN: Mr. Charles M. Christensen  
NAVSEA-62R2  
Crystal Plaza, Bldg. 6, Rm 806  
Washington, DC 20362

Mr. R. Beauregard  
Naval Sea Systems Command  
SEA 64E  
Washington, DC 20362

Brian Wheatley  
Atlantic Research Corp.  
7511 Wellington Road  
Gainesville, VA 22065

Mr. G. Edwards  
Naval Sea Systems Command  
Code 62R32  
Washington, DC 20362

C. Dickinson  
Naval Surface Weapons Center  
White Oak, Code R-13  
Silver Spring, MD 20910

Prof. John Deutch  
MIT  
Department of Chemistry  
Cambridge, MA 02139

David A. Flanigan  
Director, Advanced Technology  
Morton Thiokol, Inc.  
Aerospace Group  
3340 Airport Rd.  
Ogden, UT 84405

Dr. L.H. Caveny  
Air Force Office of Scientific  
Research  
Directorate of Aerospace Sciences  
Bolling Air Force Base  
Washington, DC 20332

Dr. Donald L. Ball  
Air Force Office of Scientific  
Research  
Directorate of Chemical &  
Atmospheric Sciences  
Bolling Air Force Base  
Washington, DC 20332

(DYN)

DISTRIBUTION LIST

Dr. Anthony J. Matuszko  
Air Force Office of Scientific Research  
Directorate of Chemical & Atmospheric  
Sciences  
Bolling Air Force Base  
Washington, DC 20332

Dr. Michael Chaykovsky  
Naval Surface Weapons Center  
Code R11  
White Oak  
Silver Spring, MD 20910

J.J. Rocchio  
USA Ballistic Research Lab.  
Aberdeen Proving Ground, MD 21005-5066

B. Swanson  
INC-4 MS C-346  
Los Alamos National Laboratory  
Los Alamos, New Mexico 87545

Dr. James T. Bryant  
Naval Weapons Center  
Code 3205B  
China Lake, CA 93555

Dr. L. Rothstein  
Assistant Director  
Naval Explosives Dev. Engineering Dept.  
Naval Weapons Station  
Yorktown, VA 23691

Dr. Henry Webster, III  
Manager, Chemical Sciences Branch  
ATTN: Code 5063  
Crane, IN 47522

Dr. A.L. Slafkosky  
Scientific Advisor  
Commandant of the Marine Corps  
Code RD-1  
Washington, DC 20380

Dr. H.G. Adolph  
Naval Surface Weapons Center  
Code R11  
White Oak  
Silver Spring, MD 20910

U.S. Army Research Office  
Chemical & Biological Sciences  
Division  
P.O. Box 12211  
Research Triangle Park, NC 27709

Dr. John S. Wilkes, Jr.  
FJSRL/NC  
USAF Academy, CO 80840

Dr. H. Rosenwasser  
AIR-320R  
Naval Air Systems Command  
Washington, DC 20361

Dr. Joyce J. Kaufman  
The Johns Hopkins University  
Department of Chemistry  
Baltimore, MD 21218

Dr. A. Nielsen  
Naval Weapons Center  
Code 385  
China Lake, CA 93555



(DYN)

DISTRIBUTION LIST

K.D. Pae  
High Pressure Materials Research Lab.  
Rutgers University  
P.O. Box 909  
Piscataway, NJ 08854

Prof. Edward Price  
Georgia Institute of Tech.  
School of Aerospace Engineering  
Atlanta, GA 30332

Dr. John K. Dienes  
T-3, B216  
Los Alamos National Lab.  
P.O. Box 1663  
Los Alamos, NM 87544

A.N. Gent  
Institute Polymer Science  
University of Akron  
Akron, OH 44325

Prof. R.W. Armstrong  
University of Maryland  
Dept. of Mechanical Engineering  
College Park, MD 20742

Dr. D.A. Shockey  
SRI International  
333 Ravenswood Ave.  
Menlo Park, CA 94025

Herb Richter  
Code 385  
Naval Weapons Center  
China Lake, CA 93555

Dr. R.B. Kruse  
Morton Thiokol, Inc.  
Huntsville Division  
Huntsville, AL 35807-7501

G. Butcher  
Hercules, Inc.  
P.O. Box 98  
Magna, UT 84044

G.A. Zimmerman  
Aerojet Tactical Systems  
P.O. Box 13400  
Sacramento, CA 95813

W. Waesche  
Atlantic Research Corp.  
7511 Wellington Road  
Gainesville, VA 22065

Prof. Kenneth Kuo  
Pennsylvania State University  
Dept. of Mechanical Engineering  
University Park, PA 16802

Dr. R. Bernecker  
Naval Surface Weapons Center  
Code R13  
White Oak  
Silver Spring, MD 20910

T.L. Boggs  
Naval Weapons Center  
Code 3891  
China Lake, CA 93555

(DYN)

DISTRIBUTION LIST

Dr. C.S. Coffey  
Naval Surface Weapons Center  
Code R13  
White Oak  
Silver Spring, MD 20910

D. Curran  
SRI International  
333 Ravenswood Avenue  
Menlo Park, CA 94025

E.L. Throckmorton  
Code SP-2731  
Strategic Systems Program Office  
Crystal Mall #3, RM 1048  
Washington, DC 23076

R.G. Rosemeier  
Brimrose Corporation  
7720 Belair Road  
Baltimore, MD 20742

C. Gotzmer  
Naval Surface Weapons Center  
Code R-11  
White Oak  
Silver Spring, MD 20910

G.A. Lo  
3251 Hanover Street  
B204 Lockheed Palo Alto Research Lab  
Palo Alto, CA 94304

R.A. Schapery  
Civil Engineering Department  
Texas A&M University  
College Station, TX 77843

Dr. Y. Gupta  
Washington State University  
Department of Physics  
Pullman, WA 99163

J.M. Culver  
Strategic Systems Projects Office  
SSPO/SP-2731  
Crystal Mall #3, RM 1048  
Washington, DC 20376

Prof. G.D. Duvall  
Washington State University  
Department of Physics  
Pullman, WA 99163

Dr. G. LINDSAY  
Naval Weapons Center  
Code 3858  
China Lake, CA 93555

Dr. M. Farber  
135 W. Maple Avenue  
Monrovia, CA 91016

W.L. Elban  
Naval Surface Weapons Center  
White Oak, Bldg. 343  
Silver Spring, MD 20910

Defense Technical Information Center  
Bldg. 5, Cameron Station  
Alexandria, VA 22314  
(12 copies)

Dr. Robert Polvani  
National Bureau of Standards  
Metallurgy Division  
Washington, D.C. 20234

Director  
Naval Research Laboratory  
Attn: Code 2627  
Washington, DC 20375  
(6 copies)

Administrative Contracting  
Officer (see contract for  
address)  
(1 copy)